



**CHARTER PLASTICS PE 3408/3608 PIPE  
GEOHERMAL PIPE  
PRODUCT DATA SHEET**

revised 8/07

<b>Properties</b>	<b>ASTM</b>	<b>Units</b>	<b>Typical values</b>
Material Designation as listed in PPI TR4			PE 3408/3608
Melt Index (190/21.6)	D 1238	g/10 min	8.0
Density (g/cc) black	D 1505	g/cm <sup>3</sup>	.955
Tensile Strength @ yield (ext. rate 2" per min.)	D 638	psi	>3000 (< 3500)
Secant Flexural Modulus @ 2 % Strain	D 790 as Specified In ASTM D3350	psi	>110,000 (< 160,000)
Hardness, Shore D	D 2240	-----	60
Elastic Modulus	D 638	Psi	110,000
SCG Resistance, Pent	F 1473	Hr	>100
Brittleness Temperature	D 746	°C (°F)	<-100 (<-150)
Coefficient of Linear Thermal Expansion	D 696	In/in/°F	(1.0x 10 <sup>-4</sup> )
HDB (Hydrostatic Design Basis) @ 73.4° F @ 140° F	D 2837	psi psi	1600 800
Cell Classification	D 3350	-	345464
Color Identification: (C) black	D 3350	-	Black with 2-2.5% carbon black

Charter product data sheet geo  
For Geothermal Pipe