

► PE 3408/3608 CTS – POTABLE WATER TUBING 12/06
Copper Tube Size HDPE
Black with 3 evenly spaced blue stripes

Designed for pressure applications

Water Service

ASTM D 2737

| Pressure Class | SIZE | O.D. | Minimum Wall | Weight Per 100' |
|----------------|--------|-------|--------------|-----------------|
| PC 200 DR 9 | ¾" | .875 | .097 | 10.26 |
| | 1" | 1.125 | .125 | 16.94 |
| | 1-1/4" | 1.375 | .153 | 25.35 |
| | 1-1/2" | 1.625 | .181 | 35.46 |
| | 2" | 2.125 | .236 | 60.54 |

Weight Calculations are based on PPI TR7
 Available in straight lengths, coils or mileage reels

► **PE 3408/3608 CTS - *POTABLE WATER TUBING***
Black with 3 evenly spaced blue stripes

SPECIFICATIONS:

PE 3408/3608 Resin listed in PPI TR4
1600 psi Hydrostatic Design Basis
800 psi Hydrostatic Design Stress/ PE 3408/3608 utilizes a .5 design factor
NSF Standard 14 and Standard 61
AWWA C901
ASTM D 2737
Cell Classification per ASTM D3350 = 345464E

Pressure Ratings:

All pressure ratings are a maximum PSI @ 73.4°F.
If temperatures exceed 80°F, contact Charter Plastics for a working pressure de-rating.

Joining:

Charter Plastics CTS tubing is made to ASTM D2737 Standards for outside diameter controlled pipe. Heat fusion is the preferred method for joining this pipe. All personnel conduction heat fusion should be experienced and follow guidelines published by the pipe manufacturer or by PPI in TR 33. It may also be joined with OD Mechanical fittings designed for pipe made to ASTM D2737 Standards. A stiffener should be inserted when using OD Compression type fittings.

Never use any lubricant on the pipe. Do not expose the pipe to direct flame.

Installing:

All Charter CTS tubing can be direct buried, plowed or pulled. Buried pipe must be supported by proper embedment material like sand or gravel. Refer to PPI's "Handbook of Polyethylene Pipe" and follow as local, state or federal guidelines.

This pipe is not designed for in house use or for hot water applications.

Safe Handling:

To safely handle and store polyethylene pipe, refer to PPI's "Material Handling Guide".

Disinfection:

New water mains and service lines should be disinfected according to AWWA C651. The disinfection should take place after the initial flushing and pressure testing. Prolonged exposure or concentrated levels of disinfection chemicals may cause damage to the inside diameter of the pipe. The disinfection chemicals should never contain more than 12% active chlorine. Charter recommends the test duration not exceed 24 hours and that upon completion, the system be thoroughly flushed with fresh water.

Testing:

All pipe should be hydrostatically tested after installation. Pneumatic testing is not recommended.

