

► **PE 3408/3608 CTS – RECLAIMED WATER TUBING**  
**Copper Tube Size HDPE**  
**Black with 3 evenly spaced lavender stripes**

12/06

**Reclaimed Water Service – NOT for potable water**

Pressure Class	SIZE	O.D.	Minimum Wall	Weight Per 100'
PC 200 DR 9	¾"	.875	.097	10.26
	1"	1.125	.125	16.94
	1-1/4"	1.375	.153	25.35
	1-1/2"	1.625	.181	35.46
	2"	2.125	.236	60.54

OD and Min. Wall values based on ASTM D 2737  
 Weight Calculations are based on PPI TR7  
 Available in straight lengths, coils or mileage reels

<sup>1</sup> 07 PE 34083608 CTS RECLAIM LAV STRIPE



► **PE 3408/3608 CTS- *RECLAIMED WATER TUBING***  
**Black with 3 evenly spaced lavender stripes**  
**Not for Potable Water**

**SPECIFICATIONS:**

PE 3408/3608 Resin listed in PPI TR4  
1600 psi Hydrostatic Design Basis  
800 psi Hydrostatic Design Stress/PE 3408/3608 utilizes a .5 design factor.  
ASTM D 2737  
Cell Classification per ASTM D3350 = 345464E

AWWA C901 – Made to AWWA C901 Standards with one exception – Resin Formulation is **not** approved for drinking water.

**Pressure Ratings:**

All pressure ratings are a maximum PSI @ 73.4°F.  
If temperatures exceed 80°F, contact Charter Plastics for a working pressure de-rating.

**Joining:**

Charter Plastics CTS tubing is made to ASTM D2737 Standards for outside diameter controlled pipe. Heat fusion is the preferred method for joining this pipe. All personnel conducting heat fusions should be experienced and follow the guidelines published by the pipe manufacturer or by PPI in TR 33. CTS may also be joined with OD Mechanical fittings designed for pipe made to ASTM D2737 Standards. A stiffener should be inserted when using OD Compression type fittings.  
Never use any lubricant on the pipe. Do not expose the pipe to direct flame.

**Installing:**

All Charter CTS tubing can be direct buried, plowed or pulled. Buried pipe must be supported by proper embedment material like sand or gravel. Refer to PPI's "Handbook of Polyethylene Pipe" and follow as local, state or federal guidelines.

This pipe is not designed for in house use or for hot water applications.

**Safe Handling:**

To safely handle and store polyethylene pipe, refer to PPI's "Material Handling Guide".

**Disinfection:**

New water mains and service lines should be disinfected according to AWWA C651. The disinfection should take place after the initial flushing and pressure testing. Prolonged exposure or concentrated levels of disinfection chemicals may cause damage to the inside diameter of the pipe. The disinfection chemicals should never contain more than 12% active chlorine. Charter recommends the test duration not exceed 24 hours and that upon completion, the system be thoroughly flushed with fresh water.

**Testing:**

All pipe should be hydrostatically tested after installation. Pneumatic testing is not recommended.

